

# COLLECTIE 2018

Type	Sg hardheid	Brand-norm	Dichtheid kg/m <sup>3</sup>	Hardheid 40% N	Drukweer stand 40% kPa	Rek bij breuk %	Treksterkte kPa	Kleur
------	-------------	------------	-----------------------------	----------------	------------------------	-----------------	-----------------	-------

## POLYETHER :

18H	18100			18	100	2,4	120	70	Wit
20Z	20065			20	65	1,6	240	90	Wit
20M	20090			20	90	2,4	220	100	Wit
25SZ	25050			25	50	1,3	300	100	Wit
25Z	25090			25	90	2,0	250	120	Wit
25H	25170			25	170	4,0	150	100	Grijs
30Z	30135			30	135	3,3	250	140	Beige
30M	30160			30	160	4,0	210	140	Geel
30H	30180			30	180	4,6	170	120	Wit
35M	35180			35	180	4,5	170	130	Blauw
35H	35220			35	200	5,0	170	150	L.Blauw
38HH	38280			38	280	7,0	180	160	Wit
40HH	40220			40	220	5,2	160	140	Wit
50SH	50320			50	320	8,0	90	120	Geel
65SH	65470			65	470	11,0	80	150	Grijs

## KOUD(HR)SCHUIM:

KS30Z	30090			30	90	2,2	180	110	Beige
KS35Z	35060			35	60	1,8	110	80	Blauw marmer
KS38M	38145	1) 2)		38	145	3,6	100	100	Oker
KS40EZ	40095	2)		40	95	2,6			Blauw marmer
KS40Z	40120	2)		40	120	3,0	160	115	Roze
KS40H	40190	2)		40	190	4,7	145	145	Bruin
KS44H	44160	1) 2)		44	160	4,0	100	90	Wit
KS50Z	50120	2)		50	130	3,3	100	80	Oker
KS50H	50160	2)		50	165	4,2	120	120	Geel

## CMHR-SCHUIM :



CMHR27Z	27080	3)		27	80	2,0	120	70	Beige
CMHR35M	35150	3)		35	150	3,8	120	110	Grijs
CMHR40H	40160	3)		40	160	4,0	140	120	Oker
CMHR50H	50180	3)		50	180	4,5	120	130	Wit
CMHR60EH	60240	3)		60	240	5,9	120	100	Wit
CMHR65SH	65340	3)		65	340	8,0	110	150	Wit

## PANTERA-SCHUIM:



PAN 50	40065	1) 2)		40	65	1,6	155	75	Creme
PANI00	50110	1) 2)		50	110	2,7	130	70	Marmer
PANI30	50140	1) 2)		50	140	3,7	120	90	Marmer
PANI50	50170	1) 2)		50	170	4,3	120	105	Marmer
PANI70	50230	1) 2)		50	230	6,0	120	105	Marmer

## CALIPORE OUTDOOR:



CALOS	S			28	100	2,6	150	70	Creme
CALOF	M			28	125	3,2	150	85	Beige
CALOM	F			29	165	4,2	130	90	L. Geel
CALOXF	XF			29	265	7,0	75	95	L. Geel

## SPECIALTIES/PLAATWERK:

SENSUS	42			42	50		180+	100+	Wit
HR 45055	45220	2)		45	220	5,5			Orchidee
HR 50065	50250	2)		50	250	6,5			Grijs
LS 55042	55160	2)		55	160	4,2			L. Grijs

1) voldoet aan de California A- en D-test

2) voldoet aan de FMVSS 302-norm

3) CMHR voldoet aan de brandtesteisen van UK SI No. 1324, 1988 (ST No. 2358 Amend 1989) (BS5852 Part2 crib 5)